



Tamilnadu Newsprint and Papers Ltd,
67, Mount Road, Guindy, Chennai 600 032, India.
Ph: 044-22354415 Email: mktg.co@tnpl.co.in

Date : 01/08/2023

AURA CELEBRATION (AUC)					
Grade : FBB - Uncoated			Shade : Natural White		
SUBSTANCE, g/m ² (TAPPI T 410)	CALIPER, μm (TAPPI T 411)	BULK, cm ³ /g	BENDING STIFFNESS, mN (TAPPI T 556)		
			MD	CD	GM
TOLERANCE : ±3%	TOLERANCE : ±5%	TOLERANCE : ±5%	TOLERANCE : ±15%		
170	289	1.70	120	55	80
190	323	1.70	160	70	105
200	340	1.70	188	82	125
210	357	1.70	218	95	145
230	391	1.70	230	105	155
250	425	1.70	320	140	210
280	476	1.70	360	160	240

PROPERTY		TOLERANCE	VALUE
MOISTURE, % (TAPPI T 412)	Up to 300 GSM	-	6.0 to 7.0
	Above 300 GSM	-	7.0 to 8.0
SMOOTHNESS, ml/min (TAPPI T 479)	Top / Bottom	Max	200/500
PLYBOND, J/m ² (TAPPI T 569)	-	Min	150
COBB ₆₀ , g/m ² (TAPPI T 441)	Top / Bottom	Max	40/40
BRIGHTNESS, % (ISO 2470)	Top	Min	77

NOTE:

1. The results of the properties are as per TNPL lab test measurements according to International standard test methods mentioned.
2. Conforming to BFR XXXVI, IS6615.
3. USFDA Compliant as per USFDA 21.CFR.176.170
4. Tolerance are based on 95% confidence limits of measurements of conditioned sample

Board Construction

