



Tamilnadu Newsprint and Papers Ltd,
67, Mount Road, Guindy, Chennai 600 032, India.
Ph: 044-22354415 Email: mktg.co@tnpl.co.in

Date : 01/08/2023

AURA CELEBRATION PLUS (ACP)					
Grade : FBB - Uncoated			Shade : Natural White		
SUBSTANCE, g/m ² (TAPPI T 410)	CALIPER, μm (TAPPI T 411)	BULK, cm ³ /g	BENDING STIFFNESS, mN (TAPPI T 556)		
			MD	CD	GM
TOLERANCE : ±3%	TOLERANCE : ±5%	TOLERANCE : ±5%	TOLERANCE : ±15%		
170	286	1.68	115	50	76
190	319	1.68	160	70	106
200	336	1.68	188	82	124
210	353	1.68	218	95	144
230	386	1.68	250	110	166
250	420	1.68	368	160	243

PROPERTY		TOLERANCE	VALUE
MOISTURE, % (TAPPI T 412)	Up to 300 GSM	-	6.0 to 7.0
	Above 300 GSM	-	7.0 to 8.0
SMOOTHNESS, ml/min (TAPPI T 479)	Top / Bottom	Max	250/250
PLYBOND, J/m ² (TAPPI T 569)	-	Min	150
COBB ₆₀ , g/m ² (TAPPI T 441)	Top / Bottom	Max	40/40
BRIGHTNESS, % (ISO 2470)	Top	Min	77

NOTE:

1. The results of the properties are as per TNPL lab test measurements according to International standard test methods mentioned.
2. Conforming to BFR XXXVI, IS6615.
3. USFDA Compliant as per USFDA 21.CFR.176.17C
4. Tolerance are based on 95% confidence limits of measurements of conditioned sample

Board Construction

